

Product datasheet

Property*	Basis Weight	SCT CD	CMT	S Test	Moisture
Method	ISO 536	ISO 9895	ISO 7263	DIN 5014	DIN EN 20287
Unit	g/m²	kN/m	N	kN/m	%
Variation	+/- 3%	-10%	-10%	-10%	+/- 1pt
	70	1,17	82	0,45	8
	75	1,27	92	0,53	8
	80	1,37	105	0,61	8
	85	1,47	120	0,68	8
	90	1,56	135	0,76	8
	95	1,64	150	0,84	8
	100	1,73	165	0,91	8
	105	1,81	179	0,99	8
	110	1,90	187	1,06	8
	115	1,99	196	1,14	8
	120	2,05	204	1,22	8
	125	2,13	-	1,29	8
	130	2,19	-	1,37	8
	135	2,26	-	1,45	8
	140	2,32	-	1,52	8
	145	2,38	-	1,60	8
	150	2,43	-	1,68	8
	155	2,49	-	1,75	8
160	2,55	-	1,83	8	

*Values subject to production variation

Available from Q1 2023

Norske Skog Bruck production ·

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 175 g/m²
- Reel width: 800 – 2850 mm
- Reel diameter: 1450 mm

Available from Q1 2025

Norske Skog Golbey production ·

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 70 – 135 g/m²
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

www.norskeskog.com

June 2025

