# **CEBICO** *Polypropylene*

# **Technical Data Sheet**



CEBICO PP30 22RID039

# Description

CEBICO PP30 22RID039 is a natural fibre composite, primarily consisting of virgin polypropylene copolymer mixed with TMP, or thermo-mechanical pulp. The composite has very high melt flow and great processability. The composite is natural light brown and has high number of visible agglomerates.

# Other product names/terms

Bio Composite (BC), Natural Fibre Composite (NFC)

# Key features

High strength, high stiffness, low shrinkage, very low carbon footprint.

# Typical characteristics

Physical properties	Value	Unit	Test method
Specific density	970	kg/m³	ISO 1183
Shrinkage	0.8	%	ISO 294
Moisture content	< 0.3	%	Saugbrugs
Fibre content	30	%	Saugbrugs
Melt flow rate	22	g/10 min	ISO 1133, 5 kg @190 °C
Oxidation induction time	4.1	min	ISO 11357-7, 200 °C

Mechanical property	Value	Unit	Test method
Tensile modulus	2500	MPa	ISO 527-2
Tensile stress at yield	29	MPa	ISO 527-2
Tensile strain at yield	1.2	%	ISO 527-2
Tensile stress at break	36	MPa	ISO 527-2
Tensile strain at break	2.0	%	ISO 527-2
Flexural modulus	2700	MPa	ISO 178
Flexural strength	56	MPa	ISO 178
Charpy impact strength	2.4	k.I/m <sup>2</sup>	ISO 179-2 1eA @ 23 °C

## **Processing**

It is important that the composite is not processed at temperatures above 190 °C. Injection speed and pressure should be at a moderate level to minimize generated shear heat in the material to maintain correct melt temperature. Processing above recommended temperature will affect negatively on mechanical properties and colour. Holding pressure should be moderate-low.

## Chemical composition

Primary component in CEBICO PP30 22RID039 is polypropylene copolymer, where 30% of the total weight is substituted with thermo-mechanical pulp. Dispersed into the plastic polymer, the TMP reinforces the polymer matrix for improved mechanical properties.

# **Packaging**

Big bags (< 1% m.c) or 25 kg bags (< 1% m.c), or in bulk.

Address:	Contact info:	Doc:
Norske Skog Saugbrugs	Tel.: + 47 69 17 40 00	Version: Jan2023-1.0A
Tistedalsgata 9-11	Email: cebico@norskeskog.com	File: CEBICO PP30 22RID039
1772 Halden - Norway		Technical Data Sheet

# **CEBICO** *Polypropylene*

# **Technical Data Sheet**



CEBICO PP30 22RID039

# Recycling

CEBICO PP30 22RID039 can be grinded, melted and remoulded like standard polypropylene.

## Environment

Comparing CEBICO PP30 22RID039 to average virgin material, the carbon footprint is reduced by up to 30%. CEBICO can replace normal plastic and glass fibre reinforced plastic as a more environmentally friendly alternative. The TMP fibres are produced from renewable and certificated raw materials and has very low carbon footprint additional to being processed using clean electric energy.

Contact us for more in-depth information about environmental impact of CEBICO natural fibre composites.

## Storage

Avoid prolonged exposure to UV-light, extreme temperatures and high humidity. Store in ambient room temperature. Improper storage can have negative effects on physical, visual and mechanical properties.

## Shelf life

Follow CEBICO storage instructions will maximize the shelf life of the material, maintain optimal properties and minimize degradation.

### Disclaimer

The information in this document is provided in good faith and to the best of our knowledge accurate and reliable as of the date of publication. We do not assume any liability, direct or indirect with respect to shelf life, performance, suitability or fitness for intended use in any application. Each customer must determine the suitability of the material for their particular use through appropriate testing and analysis. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

### Contact:

For any inquires, technical or sales, please contact by sending email to <a href="mailto:cebico@norskeskog.com">cebico@norskeskog.com</a>