

Product datasheet

Property*	Basis Weight	CMT 30 guaranteed values	CMT 30 typical values	SCT CD guaranteed values	SCT CD typical values
Method	ISO 536	ISO 7236-1	ISO 7236-1	ISO 9895	ISO 9895
Unit	g/m ²	N	N	kNm	kNm
Variation	+/- 3%				
	70	74	82	0,88	1,10
	75	86	92	1,00	1,20
	80	95	105	1,15	1,28
	85	110	120	1,27	1,36
	90	125	135	1,35	1,44
	95	140	150	1,42	1,52
	100	155	165	1,50	1,60
	105	168	179	1,58	1,68
	110	176	187	1,65	1,76
	115	184	196	1,73	1,84
	120	192	204	1,80	1,92
	125	200	213	1,88	2,01
	130	208	221	1,95	2,09
	135	216	230	2,03	2,17
	140	224	238	2,10	2,25
	145	232	247	2,18	2,33
	150	240	255	2,25	2,41
	155	248	264	2,33	2,49
	160	256	272	2,40	2,57

Moisture: 8% (+/- 1)

*Forecast values subject to production variation

Available from Q4 2022

Norske Skog Bruck production ·

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 160 g/m²
- Reel width: 800 – 2850 mm
- Reel diameter: 1400 mm

Also available from Q4 2023

Norske Skog Golbey production ·

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 70 – 135 g/m²
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

www.norskeskog.com

October 2021



launch into
a new sphere