

## Product datasheet

Property*	Basis Weight	Burst guaranteed values	Burst typical values	SCT CD guaranteed values	SCT CD typical values
Method	ISO 536	ISO 2758	ISO 2758	ISO 9895	ISO 9895
Unit	g/m <sup>2</sup>	kPa	kPa.m <sup>2</sup> /g	kNm	kNm
Variation	+/- 3%				
	70	131	145	0,94	1,15
	75	143	159	1,01	1,23
	80	155	172	1,08	1,30
	85	167	185	1,15	1,38
	90	178	198	1,22	1,45
	95	190	211	1,28	1,52
	100	200	223	1,35	1,60
	105	210	235	1,42	1,67
	110	220	247	1,49	1,75
	115	230	259	1,55	1,82
	120	240	271	1,62	1,91
	125	250	283	1,69	1,98
	130	260	295	1,76	2,05
	135	270	306	1,82	2,12
	140	280	318	1,89	2,20
	145	290	329	1,96	2,27
	150	300	341	2,03	2,35
	155	310	352	2,09	2,44
	160	320	364	2,16	2,53

Moisture: 8% (+/- 1)

\*Forecast values subject to production variation

### Available from Q4 2022

#### Norske Skog Bruck production ·

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 160 g/m<sup>2</sup>
- Reel width: 800 – 2850 mm
- Reel diameter: 1400 mm

### Also available from Q4 2023

#### Norske Skog Golbey production ·

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 70 – 135 g/m<sup>2</sup>
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

[www.norskeskog.com](http://www.norskeskog.com)

October 2021

