

Product datasheet

Property*	Basis Weight	SCT CD	CMT	Moisture
Method	ISO 536	ISO 9895	ISO 7236-1	
Unit	g/m ²	kN/m	N	%
Variation	+/- 3%	-10%	-10%	+/- 1%
	70	1,17	82	8
	75	1,27	92	8
	80	1,37	105	8
	85	1,47	120	8
	90	1,56	135	8
	95	1,64	150	8
	100	1,73	165	8
	105	1,81	179	8
	110	1,90	187	8
	115	1,99	196	8
	120	2,05	204	8
	125	2,13	213	8
	130	2,19	221	8
	135	2,26	230	8
	140	2,32	238	8
	145	2,38	247	8
	150	2,43	255	8
	155	2,49	264	8
	160	2,55	272	8

*Forecast values subject to production variation

Available from Q4 2022

Norske Skog Bruck production ·

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 160 g/m²
- Reel width: 800 – 2850 mm
- Reel diameter: 1400 mm

Also available from Q4 2023

Norske Skog Golbey production ·

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 70 – 135 g/m²
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

www.norskeskog.com

May 2022



launch into
a new sphere