

# Technical Data Sheet

CEBICO LDPE20 22RID019



## Description

CEBICO LDPE20 22RID019 is a natural fibre composite, primarily consisting of low-density polyethylene mixed with 20% TMP, or thermo-mechanical pulp. The composite is a soft grade with high melt flow for easy mouldability of complex and thin parts. The material is natural light brown and has moderate-high number of visible agglomerates. CEBICO LDPE20 22RID019 have well balanced properties for improved toughness.

## Other product names/terms

Bio Composite (BC), Natural Fibre Composite (NFC)

## Key features

Very soft, tough, low shrinkage, low carbon footprint, high melt flow, visible agglomerates

## Typical characteristics

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test method</b>
Specific density	960	kg/m <sup>3</sup>	ISO 1183
Shrinkage	0.8	%	ISO 294
Moisture content	< 0.2	%	Saugbrugs
Fibre content	20	%	Saugbrugs
Melt flow rate	30	g/10 min	ISO 1133, 5 kg @190 °C
Oxidation induction time	2	min	ISO 11357-7, 200 °C

<b>Mechanical property</b>	<b>Value</b>	<b>Unit</b>	<b>Test method</b>
Tensile modulus	530	MPa	ISO 527-2
Tensile stress at yield	8.1	MPa	ISO 527-2
Tensile strain at yield	5	%	ISO 527-2
Tensile stress at break	8.1	MPa	ISO 527-2
Tensile strain at break	5	%	ISO 527-2
Flexural modulus	360	MPa	ISO 178
Flexural strength	10	MPa	ISO 178
Charpy impact strength	9.3	kJ/m <sup>2</sup>	ISO 179-2, 1eA @ 23 °C

## Processing

Before use the material should be dried at 80 °C for minimum 1 hour. It is recommended to process the material at 190 °C or lower. It is important that the composite is not processed at temperatures above 190 °C. Injection speed and pressure should be at a moderate level to minimize generated shear heat in the material to maintain correct melt temperature. Processing above recommended temperature will affect negatively on mechanical properties and colour.

## Chemical composition

Primary component in CEBICO LDPE20 22RID019 is virgin low-density polyethylene. 20% of the total weight is substituted with thermo-mechanical pulp. Dispersed into the plastic polymer, the TMP reinforces the polymer matrix for improved mechanical properties. Additional additives have been added for improved performance, stability and compatibility.

Address: Norske Skog Saugbrugs Tistedalsgata 9-11 1772 Halden - Norway	Contact info: Tel.: + 47 69 17 40 00 Email: cebico@norskeskog.com	Doc: Version: Nov2022-1.0A File: CEBICO LDPE20 22RID019 Technical Data Sheet
---	---	---

# Technical Data Sheet

CEBICO LDPE20 22RID019



## *Packaging*

Big bags (< 1% m.c) or 25 kg bags (< 1% m.c), or in bulk.

## *Recycling*

CEBICO can be grinded, melted and remoulded like standard thermoplastic.

## *Environment*

Comparing CEBICO to average virgin material, the carbon footprint is reduced by up to 20%. The TMP fibres are produced from renewable and certificated raw materials and has very low carbon footprint additional to being processed using clean electric energy.

Contact us for more in-depth information about environmental impact of CEBICO natural fibre composites.

## *Storage*

Avoid prolonged exposure to UV-light, extreme temperatures and high humidity. Store in ambient room temperature. Improper storage can have negative effects on physical, visual and mechanical properties.

## *Shelf life*

Follow CEBICO storage instructions will maximize the shelf life of the material, maintain optimal properties and minimize degradation.

## *Disclaimer*

The information in this document is provided in good faith and to the best of our knowledge accurate and reliable as of the date of publication. We do not assume any liability, direct or indirect with respect to shelf life, performance, suitability or fitness for intended use in any application. Each customer must determine the suitability of the material for their particular use through appropriate testing and analysis. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

## *Contact:*

For any inquires, technical or sales, please contact by sending email to [cebico@norskeskog.com](mailto:cebico@norskeskog.com)



Address: Norske Skog Saugbrugs Tistedalsgata 9-11 1772 Halden - Norway	Contact info: Tel.: + 47 69 17 40 00 Email: <a href="mailto:cebico@norskeskog.com">cebico@norskeskog.com</a>	Doc: Version: Nov2022-1.0A File: CEBICO LDPE20 22RID019 Technical Data Sheet
---	--	---