

Bruck Norcote Satin

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Product Family: Norcote

Printing method: Heat set web offset

Characterization data: Fogra 46

Finish: Silk

Producer: Bruck

Basic properties	ISO								
Basis Weight	(ISO 536)	(g/m ²)	54*	57*	60*	65*	70*	80*	
Thickness	(ISO 534)	(μm)	54	57	59	62	67	72	
Bulk	(ISO 534)	(cm ³ /g)	1.0	1.0	0.98	0.95	0.96	0.90	
Brightness D65	(ISO 2470)	(%)	77	77	77	78	78	78	
CIE Whiteness	(ISO 11475)	(%)	72	72	72	73	73	73	
L-value D65	(ISO 5631-2)	(D65/10°)	91	91	91	92	92	92	
a-value D65	(ISO 5631-2)	(D65/10°)	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2	
b-value D65	(ISO 5631-2)	(D65/10°)	1.3	1.3	1.3	1.3	1.3	1.3	
Opacity	(ISO 2471)	(%)	91	92	93	94	94	95	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	7	11	14	15	17	20	

Last Updated: 30/04/2026