

Bruck Norcote Silk

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Product Family: Norcote

Printing method: Heat set web offset

Characterization data: Fogra 45L

Finish: Silk

Producer: Bruck

Basic properties	ISO									
Basis Weight	(ISO 536)	(g/m ²)	54	57	60	65	70	75*	80	90
Thickness	(ISO 534)	(µm)	62	59	60	63	66	70	73	80
Bulk	(ISO 534)	(cm ³ /g)	1.15	1.04	1.00	0.97	0.94	0.93	0.9125	0.92
Brightness D65	(ISO 2470)	(%)	87	87	88	89	90	90	90	91
CIE Whiteness	(ISO 11475)	(%)	100	100	103	105	105	108	108	108
L-value D65	(ISO 5631-2)	(D65/10°)	92	92	92	93	93	94	94	94
a-value D65	(ISO 5631-2)	(D65/10°)	0	0	0.2	0.5	0.5	0.5	0.7	0.7
b-value D65	(ISO 5631-2)	(D65/10°)	-4	-4	-4.5	-4.7	-5.0	-5.5	-5.0	-5.4
Opacity	(ISO 2471)	(%)	92	92	93	93	94	95	95	96
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	7	11	14	16	17	19	20	20
Smoothness PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5

Last Updated: 28/04/2026