

# Bruck Norcote Silk

**Anwendung:** Magazines, catalogues, supplements, direct mail, inserts/flyers

**Produktfamilie:** Norcote

**Druckverfahren:** Heat set web offset

**Characterization data:** Fogra 45L

**Oberfläche:** Silk

**Hersteller:** Bruck

Grundlegende Merkmale	ISO									
Flächenbezogene Masse	(ISO 536)	(g/m <sup>2</sup> )	54	57	60	65	70	75*	80	90
Dicke	(ISO 534)	(µm)	62	59	60	63	66	70	73	80
Spez. Volumen	(ISO 534)	(cm <sup>3</sup> /g)	1.15	1.04	1.00	0.97	0.94	0.93	0.9125	0.92
Weisse, D65/10 (UV)	(ISO 2470)	(%)	87	87	88	89	90	90	90	91
Weisse CIE	(ISO 11475)	(%)	100	100	103	105	105	108	108	108
L*	(ISO 5631-2)	(D65/10°)	92	92	92	93	93	94	94	94
a*	(ISO 5631-2)	(D65/10°)	0	0	0.2	0.5	0.5	0.5	0.7	0.7
b*	(ISO 5631-2)	(D65/10°)	-4	-4	-4.5	-4.7	-5.0	-5.5	-5.0	-5.4
Opazität	(ISO 2471)	(%)	92	92	93	93	94	95	95	96
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	7	11	14	16	17	19	20	20
Glätte	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5

*Last Updated: 28/04/2026*