

Bruck Norcote Super

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Product Family: Norcote

Printing method: Heat set web offset

Characterization data: Fogra 45L

Finish: Gloss

Producer: Bruck

Basic properties	ISO										
Basis Weight	(ISO 536)	(g/m ²)	54*	57	60	65	70	75	80	90	
Thickness	(ISO 534)	(μm)	51	52	53	55	58	62	67	75	
Bulk	(ISO 534)	(cm ³ /g)	0.94	0.91	0.88	0.85	0.83	0.83	0.84	0.83	
Brightness D65	(ISO 2470)	(%)	86	86	87	88	89	90	90	91	
CIE Whiteness	(ISO 11475)	(%)	99	101	102	104	105	107	107	108	
L-value D65	(ISO 5631-2)	(D65/10°)	92	92	92	92	92	93	93	94	
a-value D65	(ISO 5631-2)	(D65/10°)	0	0	0.2	0.6	0.6	0.7	0.6	0.7	
b-value D65	(ISO 5631-2)	(D65/10°)	-4	-4.5	-4.5	-4.8	-5.0	-5.3	-5.0	-5.5	
Opacity	(ISO 2471)	(%)	90	92	92	93	94	94	95	96	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	35	40	43	46	50	50	50	50	
Smoothness PPS 10	(ISO 8791-4)	(μm)	1.3	1.3	1.2	1.2	1.2	1.2	1.2	1.2	

Last Updated: 28/04/2026