

Bruck Norcote Top

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Product Family: Norcote

Printing method: Heat set web offset

Characterization data: Fogra 45L

Finish: Gloss

Producer: Bruck

Basic properties	ISO									
Basis Weight	(ISO 536)	(g/m ²)	65	70	75*	80	90	100	110	115
Thickness	(ISO 534)	(μm)	55	58	62	66	75	84	95	104
Bulk	(ISO 534)	(cm ³ /g)	0.85	0.83	0.83	0.83	0.83	0.84	0.86	0.90
Brightness D65	(ISO 2470)	(%)	94	95	96	97	97	97	97	98
CIE Whiteness	(ISO 11475)	(%)	120	120	121	123	125	125	125	125
L-value D65	(ISO 5631-2)	(D65/10°)	92	94	94	94	94	94	94	94
a-value D65	(ISO 5631-2)	(D65/10°)	0.5	0.6	0.6	0.7	0.6	0.7	0.7	0.7
b-value D65	(ISO 5631-2)	(D65/10°)	-7.7	-8.0	-8.0	-8.0	-8.5	-8.6	-8.6	-9.0
Opacity	(ISO 2471)	(%)	92	93	94	95	96	96	97	97
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	48	53	53	53	54	55	55	55
Smoothness PPS 10	(ISO 8791-4)	(μm)	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2

Last Updated: 28/04/2026