

# Bruck Norcote Top

**Anwendung:** Magazines, catalogues, supplements, direct mail, inserts/flyers

**Produktfamilie:** Norcote

**Druckverfahren:** Heat set web offset

**Characterization data:** Fogra 45L

**Oberfläche:** Gloss

**Hersteller:** Bruck

Grundlegende Merkmale	ISO									
Flächenbezogene Masse	(ISO 536)	(g/m <sup>2</sup> )	65	70	75*	80	90	100	110	115
Dicke	(ISO 534)	(µm)	55	58	62	66	75	84	95	104
Spez. Volumen	(ISO 534)	(cm <sup>3</sup> /g)	0.85	0.83	0.83	0.83	0.83	0.84	0.86	0.90
Weisse, D65/10 (UV)	(ISO 2470)	(%)	94	95	96	97	97	97	97	98
Weisse CIE	(ISO 11475)	(%)	120	120	121	123	125	125	125	125
L*	(ISO 5631-2)	(D65/10°)	92	94	94	94	94	94	94	94
a*	(ISO 5631-2)	(D65/10°)	0.5	0.6	0.6	0.7	0.6	0.7	0.7	0.7
b*	(ISO 5631-2)	(D65/10°)	-7.7	-8.0	-8.0	-8.0	-8.5	-8.6	-8.6	-9.0
Opazität	(ISO 2471)	(%)	92	93	94	95	96	96	97	97
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	48	53	53	53	54	55	55	55
Glätte	(ISO 8791-4)	(µm)	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2

*Last Updated: 28/04/2026*