

Bruck Norcote

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Product Family: Norcote

Printing method: Heat set web offset

Characterization data: Fogra 46

Finish: Gloss

Producer: Bruck

Basic properties		ISO							
Basis Weight	(ISO 536)	(g/m ²)	51	54	57	60	65	70	80
Thickness	(ISO 534)	(μm)	49	51	52	53	56	58	66
Volume	(ISO 534)	(kg/m ³)	0.96	0.94	0.91	0.88	0.86	0.83	0.83
Brightness D65	(ISO 2470)	(%)	76	77	77	77	78	78	80
CIE Whiteness	(ISO 11475)	(%)	69	72	72	72	73	73	76
L-value D65	(ISO 5631-2)	(D65/10°)	90	91	91	91	92	92	92
a-value D65	(ISO 5631-2)	(D65/10°)	-0.4	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2
b-value D65	(ISO 5631-2)	(D65/10°)	1.5	1.3	1.3	1.3	1.3	1.3	1.3
Opacity	(ISO 2471)	(%)	90	91	92	93	93	93	95
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	32	35	40	45	48	50	51
Smoothness PPS 10	(ISO 8791-4)	(μm)	1.3	1.3	1.3	1.2	1.2	1.2	1.2

Last Updated: 28/04/2026