

Saugbrugs NorSC Lite

Anwendung: Magazines, inserts, catalogues, direct mail and door drop.

Product Family: SC

Produktfamilie: Nor

Druckverfahren: Heatset & Rotogravure

Characterization data: Fogra 40

Oberfläche: Gloss

Hersteller: Saugbrugs

| Grundlegende Merkmale | ISO | | | | | | | | |
|-----------------------|--------------|----------------------|------|------|------|------|------|------|------|
| Flächenbezogene Masse | (ISO 536) | (g/m ²) | 37* | 39 | 42 | 45 | 47.4 | 52 | 56 |
| Dicke | (ISO 534) | (µm) | 39 | 43 | 44 | 45 | 46 | 48 | 49 |
| Blattdichte | (ISO 534) | (kg/m ³) | 950 | 960 | 980 | 1015 | 1030 | 1130 | 1140 |
| Spez. Volumen | (ISO 534) | (cm ³ /g) | 1.05 | 1.04 | 1.03 | 1.01 | 0.97 | 0.88 | 0.88 |
| Weisse, D65/10 (UV) | (ISO 2470) | (%) | 69 | 69 | 69 | 69 | 69 | 69 | 69 |
| Weisse CIE | (ISO 11475) | (%) | 52 | 52 | 52 | 52 | 52 | 52 | 52 |
| L* | (ISO 5631-2) | (D65/10°) | 88 | 88 | 88 | 88 | 88 | 88 | 88 |
| a* | (ISO 5631-2) | (D65/10°) | -1.4 | -1.4 | -1.4 | -1.4 | -1.4 | -1.4 | -1.4 |
| b* | (ISO 5631-2) | (D65/10°) | 4.3 | 4.3 | 4.3 | 4.3 | 4.3 | 4.3 | 4.3 |
| Opazität | (ISO 2471) | (%) | 87 | 88 | 89 | 90 | 91 | 93 | 94 |
| Glanz (Hunter) | (ISO 8254-1) | (%) | 37 | 37 | 37 | 37 | 39 | 39 | 39 |
| Glätte | (ISO 8791-4) | (µm) | 1.3 | 1.3 | 1.3 | 1.2 | 1.2 | 1.1 | 1.1 |

Last Updated: 16/01/2023